Photo Papers



1929B Glacier Photo Quality Paper FSC® 300 g/m²

Product Description

This top quality photo inkjet paper has a quality photo coating for high grade natural colour prints of graphic pictures, presentations and photos. The paper is instant dry, is smudge resistant and provides good colour density and excellent image sharpness. This paper is compatible with a large range of dye and pigment digital printing systems, and is the most ideal product for users who need top quality photographic reproductions.

Physical Properties

Thickness 288 μm ISO 534 Gloss 47% ISO 21974 Weight 300 g/m² ISO 536 Whiteness 120 CIE ISO 11475

All values listed are target values

Features / Applications

Extremely quick drying
Dye and pigment ink
compatible
Good Colour Density
Excellent Image Sharpness

Smudge Resistant Lamination not necessary Easy handling

Easy handling FSC® certified

Photography
Portraits
Posters

Graphic Art Reproductions Exhibition graphics

Indoor and Outdoor signage

Available Widths (mm)

2" core 432 610 914 1067 1524

Refer for our current offering to www.canon-europe.com/mediaguide

Storage Conditions

Store paper only in original boxes, out of direct sunlight and under normal climatic conditions (23 °C, 50% RH) until ready to use. Allow material to adapt to room conditions before use. Papers can absorb moisture in humid conditions or lose moisture in low humidity conditions. Highly humid conditions make the ink drying time longer and this could interfere with proper laminate adhesion.

Environment, Health & Safety

No Material Safety Data Sheet required. Paper waste not suitable for recycling.

Lamination Compatibility

Cold Warm Hot yes yes no

Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C

Shelf life

Two years from shipping date when stored under ideal conditions (see above)

Colour Profiles Canon develops high-quality colour profiles for media / ink / printer / RIP combinations. Check availability of profiles for your printer on www.canon-europe.com/mediaguide

Environmental Certification





Processing Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing. Side to be printed is the outer side of the roll.

Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects. It is recommended to handle the media with cotton gloves.

Insert the paper with care in the printer. Incorrect loading can cause skewing or creasing. It is recommended to calibrate the printer before printing and to make a test print.

Print results will vary for different printer ink combinations. Ink restrictions and printer settings should be set for specific printer-ink combinations to obtain the best results.

Canon media profiles include optimal ink and printer settings for Canon supported printers. Depending on fluctuations in environment, printer, ink, media and applications, printer parameters may have to be adjusted slightly, to obtain the best results.

The use of dye inks can lead to premature fading of colors.

Recommended media settings on Canon printers:

Operation Panel: HW Satin Photo

Printer Driver: Canon HW Satin Photo Paper

Application guidelines

To add surface protection from dirt, abrasion and gas-fading, lamination is recommended. Although ink drying is virtually immediate, it is still recommended to allow a waiting time of approximately 3 hours before lamination. In order to prevent moisture ingress and paper splitting, lamination with a 5-6 mm encapsulated edge is also recommended. Laminate must be evenly applied to the print in order to avoid curling. Both hot and cold lamination is possible.

Standard disclaimer: All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.

Canon Inc. canon.com Canon Europe canon-europe.com English edition 0615 © Canon Europa N.V., 2019

